Technical data sheet

Reference No:

0

20


30

40

Product: VRX - AFS35

Appearance: Silica Sand


Main Application: Foundry



50







Note: Indicative grading only. Grading analysis may vary from time to time due to changes in raw feed.

100

140

200

70

CIEVE CIZE	TYPICAL	. VALUES	
SIEVE SIZE	% RETAINED	% PASSING	
ASTM SIEVE	INDIVIDUAL	CUMULATIVE	
SERIES NUMBER	INDIVIDORE	CONICERTIVE	
16	0.0	100.0	
20	0.0	100.0	
30	0.9	99.1	
40	56.67	42.4	
50	39.2	3.3	
70	3.2	0.0	
100	0.0	0.0	
140	0.0	0.0 0.0	
200	0.0		
270	0.0	0.0	
Pan	0.0	0.0	
	AFS	35.0	

Chemical composition (All results in %)

The following properties listed below are to be used as guidelines only. Minor variation to these is to be expected due to slight variations in raw feed

SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	CaO	MgO	K ₂ O
99.5	0.5	0.060	0.050	0.01	0.002	0.03

Physical properties

Density	Hardness	Colour	Ph	Moisture	LOI
2.65	7	Yellow	7	<5%	0.1

DISCLAIMER: The information set forth in this Technical Data Sheet represents actual properties of the product sampled. The information listed as the typical chemical analysis is supplied as a guide only.

Note: Please remember product segregation can occur through transport and handling.